

## FLUSH E/C SAMPLING KIT

(ABS019F-EC - 25mm)

This component is used when it is necessaty to sample through a suspended ceiling. The capillary end cap fits onto the end of the pipe run. There is then a 2 meter 10mm OD nylon tube which links into the flush sampling head, which is fixed by a nylon nut/washer to the ceiling tile.

## **Installation Instructions:**

Use the correct solvent Plusbond 3019. Do not paint.

Keep pipe clean and free from dust. Do not install in direct sunlight. Only install with approved pipe. Do not use solvents to clean, only soapy water.

ABS019F-EC - 25mm Part No.

**Fitting colour RED** 

**Diameter Tolerance** +/- 0.15mm



**RAW MATERIAL DATA** 

Kumho ABS 750 Acrylonitrile Butaduene Styrene

Specific Gravity 1.04 Test Method ASTM D792

Melt Mass - Flow Rate (MFR) 200°C/21.6 kg 47 g/10 min 200°C/5.0 kg 4.1 g/10 min 220°C/10.0 kg 34 g/10 min Test Method ASTM D1238

Molding Shrinkage -Flow 0.0040 to 0.0070 in/in Test Method ASTM D955

**Mechanical:** 

Tensile Strength Yield, 73°F (23°C) 1.97 in (50.0mm) 6670 psi Test Method ASTM D638

**Tensile Elongation** 

1.97 in (50.0 mm), 15% Test Method ASTM D638

**Flexural Modulu** 

Yield, 73°F (23°C) 0.118 in (3.00 mm 312000 psi Test Method ASTM D63

**Flexural Strength** 

Yield, 73°F (23°C) 0.118 in (3.00 mm) 9230 psi Test Method ASTM D790

Noched Izod Impact 73°F(23°C), 0.126 in (3.20 mm), 5.5 ft·lb/ir 73°F(23°C), 0.252 in (6.40 mm), 4.8 ft·lb/ir Test Method ASTM D256

Rockwell Hardness (R-Scale) 108 Test Method ASTM D785

**Deflection Temperature Under Load** 264 psi (1.8 MPa), Unanneald 185°F/85°C Test Method ASTM D648

Vicat Softening Temperature 203°F/95°C Test Method ASTM D1525

**Flamibility** Flame Rating 0.0630 in (1.60 mm) HB 0.0866 in (2.20 mm) HB 0.126 in (3.20 mm) HB Test Method UL 94

**RAW MATERIAL DATA** 

OD Tol's +0.03/-0.09mm Burst Pressure 995 PSI / 68 bar Bend Radius 40mm Weight/30m 1.08kgs

NEM 10x8 -OD Tol's +0.02/-0.10mm Burst Pressure 772 PSI / 53 bar Bend Radius 50mm Weight/30m 0.87kgs

Temperature Range --40°C to +70°C, Occasional use up to +130°C, Brittle point: -70°C

Technical information for use as a guide only.

Pressure values given are based on the short term burst pressure at 20°C based on a 3:1 safety factor. Any increase in temperature above 20°C will result in a decline in working pressure values.

Products and specifications are subject to improvements and change without

Unit 11, Eldonwall Trading Estate, St.Phillips, Bristol, BS4 3QQ

Tel: 0117-967-9999 Fax: 0117-961-9261 http://www.abspipesandfittings.co.uk

©All rights reserved. Bisson Ltd